



(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

03.01.2001 Bulletin 2001/01

(51) Int Cl.: C22C 19/05

(21) Application number: 00401832.1

(22) Date of filing: 27.06.2000

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE

Designated Extension States:

AL LT LV MK RO SI

(30) Priority: 30.06.1999 JP 18676999

27.07.1999 JP 21151999

(71) Applicant: SUMITOMO METAL INDUSTRIES, LTD.

Osaka-shi, Osaka 541-0041 (JP)

(72) Inventors:

• Nishiyama, Yoshitaka

Nishinomiya-shi, Hyogo 663-8156 (JP)

• Anraku, Toshiro

Nishinomiya-shi, Hyogo 662-0862 (JP)

• Sawaragi, Yoshiatsu

Nishinomiya-shi, Hyogo 663-8104 (JP)

• Ogawa, Kazuhiro

Nishinomiya-shi, Hyogo 662-0881 (JP)

• Okada, Hirokazu

Kobe-shi, Hyogo 651-1301 (JP)

(74) Representative: Uchida, Kenji et al

S.A. Fedit-Loriot et Autres Conseils en Propriété
Industrielle,

38, avenue Hoche

75008 Paris (FR)

(54) Heat resistant nickel base alloy

(57) A heat resistant Ni base alloy comprises, on a mass% basis, 0.1% or less C, 2% or less Si, 2% or less Mn, 0.005% or less S, 10 to 25% Cr, 2.1 to less than 4.5% Al, 0.08% or less N, 0.001 to 1% in total of one or

more elements of B: 0.03% or less, Zr: 0.2% or less and Hf: 0.8% or less, and 2.5 to 15% in total of one or more elements of Mo: 0.01 to 15% and W: 0.01 to 9%. The alloy is suitable as a material for a pipe used in ethylene cracking furnace.

Description

TECHNICAL FIELD OF THE INVENTION

[0001] The present invention relates to a heat resistant Ni base alloy having high strength at high temperature and excellent in hot workability, weldability, and carburization resistance. The alloy of the present invention is suitable in particular as a material of pipes used in naphtha reforming furnaces and ethylene cracking furnaces for producing petrochemical fundamental products such as ethylene and propylene by cracking with steam hydrocarbon materials such as naphtha, propane, ethane, and gas oil at a high temperature of 800°C or more.

RELATED BACKGROUND ART

[0002] The service temperature of the pipes used in ethylene cracking furnaces tends to be higher from the viewpoint of improving an ethylene yield ratio.

[0003] Materials of such cracking furnace pipes require high-temperature strength, carburization resistance and heat resistance because their inside is exposed to a carburization atmosphere.

[0004] On the other hand, carbon is deposited on the inside surface of a cracking furnace pipe during the operation (this phenomenon is called coking), and as the amount of carbon deposited on the inside of the pipe increases, disadvantages in operation occur, such as an increase in the internal pressure of the pipe and a reduction in the heating efficiency. Therefore, coking resistance is required. In the actual operation, the so-called decoking operation for removing deposited carbon by air or steam is periodically conducted, but the suspension of the operation and the working load are great problems.

[0005] Such coking and its related problems are more serious when the cracking furnace pipe has a smaller diameter which is advantageous for improving the yield.

[0006] JP Publication No. A 2-8336 discloses the technique of inhibiting coking in which more than 28% Cr is contained in an alloy to form a strong and stable Cr_2O_3 layer on the surface of the alloy in order to prevent the coking-promoting catalytic elements of Fe and Ni from being exposed to the surface of the alloy.

[0007] On the other hand, increasing of the Si content in an alloy is known to be effective for improving carburization resistance, as disclosed in e.g. JP Publication No. A 57-23050.

[0008] In the prior art described above, however, there are problems as follows:

[0009] When the high-Cr alloy disclosed in JP Publication No. A 2-8336 is applied as a structural member with high-temperature strength for the prevention of coking, the metal structure should be austenitized by increasing the Ni content in the alloy, but, as the result, its high-temperature strength becomes lower than that of the conventional alloy. Therefore, the application thereof as a structural member with high-temperature strength is difficult.

[0010] JP Publication No. A 2-8336 discloses that an alloy poor in high-temperature strength is combined for use with another member with high-temperature strength to form a clad tube, but the clad tube is problematic in respect to the production cost and reliability.

[0011] The present inventors found previously that the carburization resistance and coking resistance can be significantly improved by forming a strong and tight Al_2O_3 layer on the surface of a metal by increasing the content of Al in an alloy, compared with the conventional alloy, and the γ phase is finely precipitated in the matrix during the service at high temperature by increasing the content of Ni in such a high-Al alloy, and the creep rupture strength can also be significantly improved. The patent for this alloy was applied as a Ni base alloy suitable as a pipe in an ethylene cracking furnace in Japanese Patent Application No. 3-308709 (Publication No. A4-358037) and Japanese Patent Application No. 4-41402 (Publication No. A5-239577) respectively. However, in consideration of mass production on a commercial scale, an large amount of hot working was required for the production of the Ni base alloy with high-Al but the hot workability of such alloy was not satisfactory.

[0012] With respect to the Ni base alloy with an increased content of Al, alloys excellent in oxidation resistance are disclosed in JP Publication No. B 3-46535 and A 60-238434. However, the alloys disclosed in these publications are also poor in hot workability and weldability, because adequate attention was not paid to these characteristics on the design of alloying components. Further, alloys excellent in carburization resistance and high-temperature strength are also disclosed in JP Publication No. A 7-54087 and A 9-243284, but attention was not actually paid to hot workability and weldability.

DISCLOSURE OF THE INVENTION

[0013] The object of the present invention is to provide a heat resistant alloy which is excellent in carburization resistance and coking resistance under the environment where ethylene cracking furnace pipes are used, more specifically, carburization, oxidation and temperature change are repeated; and also which is excellent in hot workability

and weldability and has excellent high-temperature strength.

[0014] The summary of the present invention is as follows:

(1) A heat resistant Ni base alloy excellent in hot workability, weldability, and carburization resistance comprising, on a mass% basis, C: 0.1% or less, Si: 2% or less, S: 0.005% or less, Cr: 10 to 25%, Al: 2.1 to less than 4.5%, N: 0.08% or less, 0.001 to 1% in total of one or more elements of B: 0.03% or less, Zr: 0.2% or less and Hf: 0.8% or less, 2.5 to 15% in total of either one or both of Mo: 0.01 to 15% and W: 0.01 to 9%, Ti: 0 to 3%, Mg: 0 to 0.01%, Ca: 0 to 0.01%, Fe: 0 to 10%, Nb: 0 to 1%, V: 0 to 1%, Ta: 0 to 2%, Y: 0 to 0.1%, La: 0 to 0.1%, Ce: 0 to 0.1%, Nd: 0 to 0.1%, Cu: 0 to 5%, Co: 0 to 10%, and the balance being substantially Ni.

(2) The heat resistant Ni base alloy according to above (1), wherein the Ti content is 0.005 to 3% by mass.

(3) The heat resistant Ni base alloy according to above (1), wherein the Ti content is 0.005 to 3% and either one or both of Mg and Ca are contained in an amount of 0.0005 to 0.01% and 0.0005 to 0.01%, respectively.

(4) The heat resistant Ni base alloy according to above (1), wherein the Ti content is 0.005 to 3%, either one or both of Mg and Ca are contained in an amount of 0.0005 to 0.01% and 0.0005 to 0.01%, respectively, and Fe content is 0.1 to 10%.

(5) A heat resistant Ni base alloy comprising, on a mass% basis, C: 0.07% or less, Si: 0.01 to 1%, Mn: 1% or less, S: 0.0025% or less, Cr: 12 to 19%, Al: 2.1 to less than 3.8%, N: 0.045% or less, 0.001 to 1% in total of one or more elements of B: 0.03% or less, Zr: 0.2% or less and Hf: 0.8% or less, Mo: 2.5 to 12%, Ti: 0.005 to 1%, Ca: 0.0005 to 0.01%, Fe: 0.1 to 10%, and the balance being essentially Ni.

[0015] In order to obtain the alloy which satisfies the essential characteristics required as a commercial production alloy such as hot workability and weldability without lowering carburization resistance and coking resistance at high temperatures, the present inventors carried out extensive experiments on alloys with various chemical compositions and reached the following findings as a result.

a) Even if the Ni base alloy does not contain Al in an amount of 4.5% or more unlike the conventional alloy, an alumina-based oxide layer can be formed on the surface of the alloy containing less than 4.5% Al by means of containing not less than 10% Cr and reducing the N content, whereby excellent carburization resistance and coking resistance can be attained and also high-temperature strength is improved.

b) The N in an alloy containing not less than 1% Al easily forms Al nitride, and the alumina-based oxide layer tends to lose its protective property from this nitride precipitation which acts as the initiation point.

c) By reducing the Al content to less than 4.5%, hot workability and weldability of the Ni base alloy containing Al are improved, but compared with conventional Fe-Cr-Ni alloys or Ni-Cr alloys, are still unsatisfactory in consideration of mass production. This is because Ni-Al intermetallic compounds precipitate at the time of hot working or welding, and the inside of the grains of the alloy are significantly reinforced so that the grain boundaries are relatively weakened, which result in both a reduction of hot workability and an occurrence of a hot cracking at the time of welding. Accordingly, the reinforcement of the grain boundaries which can compete with the reinforcement of the inside of the grains is important and effective for improving hot workability and weldability.

d) On the other hand, in the Ni base alloy containing a large amount of Al, the grain boundaries are weakened and S is one of the main factors in weakening the grain boundaries. Therefore, it is important for improving hot workability to limit the S content to 0.005% or less, and further improving effects can be expected by limiting the S content to 0.003% or less.

e) Further, the elements of B, Zr and Hf enhance the binding force of grains on the grain boundaries and are effective for reinforcing the grain boundaries. Therefore, it is preferable that one or more of these elements are contained while the S content is reduced.

f) The reduction of S content as described above and the incorporation of one or more elements of B, Zr and Hf are effective for preventing the reduction of hot workability and the occurrence of hot cracking at the time of welding, but these measures only are still not satisfactory. Further, it is also important to reduce the N content to the lowest degree. This is because the N in the Ni base alloy containing a large amount of Al easily forms Al nitride as described above, and these nitrides precipitation significantly inhibit hot workability and weldability.

DETAILED DESCRIPTION OF THE INVENTION

[0016] The following describe the chemical composition of the alloy of the present invention and its effects. The term "%*" for alloying elements means % by mass.

C:

[0017] C is a very effective element which forms carbides to improve tensile strength and creep rupture strength required for heat-resistant steel. However, if the C content exceeds 0.1%, the ductility and toughness of the

[0018] alloy are significantly lowered, and further the formation of an alumina layer on the Al-containing Ni base alloy is inhibited, and thus the upper limit is defined as 0.1%. The C content is preferably 0.09% or less. The C content is more preferably 0.07% or less.

Si:

[0019] Si is an element which is important as a deoxidation element and further contributes to improvements in oxidation resistance and carburization resistance, but its effect on the Al-containing Ni base alloy is relatively low. For the Ni base alloy containing a large amount of Al, however, Si has a strong action of lowering hot workability and weldability, and thus the Si content is preferably lower when particularly, hot workability in manufacturing is regarded as important. However, in consideration of the contribution of Si to oxidation resistance and carburization resistance, the Si content must be 2% or less. Desirably, the content of Si should be 0.01 to 1.5%, more desirably 0.01 to 1%.

Mn:

[0020] Mn is an effective element as a deoxidization element but is an element promoting the formation of a spinel type oxide layer which is a major factor for deterioration of coking resistance, and thus its content should be reduced to 2% or less. Desirably, the content of Mn should be 1% or less.

S:

[0021] S is a very harmful element which is segregated on grain boundaries to weak the binding force of grains and to deteriorate hot workability, and thus, the regulation of its content upper limit is very important. Since the reinforcement of the grain boundaries is particularly important in the Al-containing Ni base alloy, S is preferably reduced to the lowest degree. To improve hot workability and weldability, the S content should be 0.005% or less. Desirably, the content of S should be 0.003% or less. More desirably, the content of S should be 0.0025% or less.

Cr:

[0022] Cr is an effective element for improving oxidation resistance and coking resistance, and has an action of forming an alumina layer uniformly at an initial stage of its formation. Further, this element also forms carbides which contribute to the improvement of creep rupture strength. In addition, Cr contributes to the improvement of hot workability in the alloying system defined in the present invention. To achieve these effects, this element should be contained in an amount of 10% or more. On the other hand, when Cr is contained in excess, the formation of a uniform alumina layer is conversely inhibited, while mechanical properties such as toughness and workability are further inhibited. Accordingly, the Cr content is defined as 10 to 25%. Preferably, the content of Cr should be 12 to 23%. More preferably, the content of Cr should be 12 to less than 20%.

Al:

[0023] Al is a very effective element for improving carburization resistance and coking resistance and further improving high-temperature strength. To achieve these effects, a corundum type alumina scale must be uniformly formed. On the other hand, a precipitation reinforcing action by forming the γ phase $[\text{Ni}_3(\text{Al}, \text{Ti})]$ intermetallic compound can be expected. To achieve these effects, an Al content of at least 1.5% is necessary. On the other hand, if the Al content is 4.5% or more, hot workability is significantly lowered. Accordingly, the Al content must be 2.1% or more to less than 4.5%. Preferably, the content of Al should be 2.1% to less than 4%, and more preferably 2.1% to less than 3.8%.

N:

[0024] The N content is one of the essential prescriptions in the present invention. In the conventional heat-resistant steel, N is effective and positively used for increasing the high temperature strength due to the solid-solution strengthening. However, in the Al-containing nickel base alloy, N cannot be expected to attain the solid-solution strengthening because of precipitation thereof as a nitride such as AlN in the alloy, and this element further significantly reduces hot workability and weldability. In addition, there is a problem that the protective layer is destroyed by the nitride as the

starting point, resulting in the deterioration of carburization resistance. However, since an excessive reduction in the N content causes an increase in costs for refining, the N content must be 0.08% or less. However, this element should essentially be reduced to the lowest degree, desirably 0.055% or less. More preferably, the content of N should be 0.045% or less.

B, Zr, Hf:

[0025] These elements are effective mainly for reinforcing grain boundaries in the alloy and contribute to improvements in hot workability and weldability, and thus one or more of these elements should be contained. However, if these elements are contained in excess, a reduction in creep rupture strength is caused, and thus the upper limits of these elements must be 0.03% for B, 0.20% for Zr, and 0.8% for Hf respectively, and their content in total must be 1%. Further, their content in total must be at least 0.001% in order to achieve the effects described above.

Mo, W:

[0026] Mo and W are effective mainly as solid solution strengthening elements, and by reinforcing the austenitic phase of the alloy, creep rupture strength is increased. If these elements are contained in excess, not only intermetallic compounds leading to a reduction in toughness are precipitated but carburization resistance and coking resistance are also deteriorated. If these elements are contained, the upper limit in terms of the total of one or more elements of Mo and W should be 15% or less. Particularly, for application to members whose creep rupture strength is regarded as important, it is effective to positively add Mo and W to demonstrate this effect. As compared with Mo, W causes a more significant reduction in hot workability and weldability due to the precipitation of intermetallic compounds, and thus the upper limit of W should be lower than that of Mo. Accordingly, the total content of Mo and/or W must be 2.5 to 15% wherein the Mo content is 0.01 to 15% and the W content is 0.01 to 9%.

Ni:

[0027] Ni is an indispensable element for achieving a stable austenitic structure and for ensuring carburization resistance, and should be contained desirably in a higher amount to increase the effect of precipitation reinforcement particularly by the γ phase.

[0028] To solve the problem of the present invention, the alloy should have at least the chemical composition described above, but the following elements may be contained as necessary.

Ti:

[0029] Ti is an element for promoting the precipitation of γ' phase to improve creep rupture strength. Further, this element also contributes to the reinforcement of grain boundaries. To achieve these effects, Ti is contained preferably in an amount of 0.005% or more. However, if it is contained in excess, the γ' phase is precipitated in excess, and thus, hot workability and weldability are significantly deteriorated. Accordingly, if Ti is contained, the content of Ti should be 3% or less. Preferably, the content of Ti should be 1% or less.

Mg and Ca:

[0030] These elements have an action of fixing a harmful S for hot workability as sulfides, thus increasing the strength of grain boundaries and improving hot workability, and therefore, these elements may be contained as necessary. To achieve these effects, each of these elements should be contained preferably in an amount of 0.0005% or more. However, if they are contained in excess, hot workability and weldability are conversely deteriorated. Accordingly, the upper limit for each of Mg and Ca should be preferably 0.01%. If these elements are to be contained, preferably, they should be contained, such that $[(1.178 \text{ Mg} + \text{Ca})/\text{S}]$ is in the range of 0.5 to 3.

Fe:

[0031] Fe improves creep elongation, increases creep rupture strength, and contributes to improvements in hot workability and workability at normal temperature. To achieve these effects, this element should be contained preferably in an amount of 0.1% or more. However, if it is contained in excess, both creep rupture strength and hot workability are lowered conversely, and thus, when it is to be contained, preferably, its content upper limit should be 10%.

Nb, V and Ta:

[0032] These elements contribute to the improvement of creep rupture strength as carbides and nitrides or as solid solutions in the austenitic phase or the γ phase. To achieve these effects, each of these elements should be contained preferably in an amount of 0.01% or more. However, if these elements are contained in excess, a reduction in toughness is caused, and thus, when these are to be contained, the upper content limits of these elements should be preferably 1% for Nb or V, respectively and 2% for Ta. When two or more of these elements are used in combination, their content in total should be desirably 3% or less.

La, Ce and Nd:

[0033] These elements may be contained as necessary because they have not only the effect of preventing the exfoliation of an alumina layer under the conditions where the alloy is repeatedly heated and cooled, but also the effect of improving carburization resistance and coking resistance for use under the environment where the temperature is fluctuated. To achieve these effects, each of these elements should be contained preferably in an amount of 0.002% or more. However, when these are contained in excess, the effect of preventing the exfoliation of an alumina layer is saturated and further the workability is worsened. Accordingly, the upper limits of La, Ce and Nd content should be preferably 0.1%, respectively. These elements may be contained alone or in combination thereof.

Cu, Co:

[0034] Cu and Co may be substituted as necessary for a part of Ni to stabilize mainly the austenitic phase. However, if these elements are added in excess, toughness and workability are deteriorated. Accordingly, the upper limit of Cu content must be 5% or less. The Cu content should be preferably 3% or less, more preferably 1.5% or less. In addition, the upper limit of Co content must be 10%. The content of Co is preferably 8% or less, more preferably 5% or less. Further, Co has an action of improving creep strength by the solid solution strengthening. The lower limit of each of these elements should be preferably 0.01% or more.

[0035] Among alloys in the range of those chemical compositions described above, an alloy particularly excellent in various characteristics has preferably the following chemical composition:

[0036] C: 0.07% or less, Si: 0.01 to 1% or less, Mn: 1% or less, S: 0.0025% or less, Cr: 12 to less than 20%, Al: 2.1 to less than 3.8%, and N: 0.045% or less, 0.001 to 1% in total of one or more metals of B: 0 to 0.03%, Zr: 0 to 0.2% and Hf: 0 to 0.8%, and Mo: 2.5 to 12%, Ti: 0.005 to 1%, Ca: 0.0005 to 0.01%, and Fe: 0.1 to 10%.

[0037] The alloy of the present invention can be obtained by conventional melting and refining process and then casting, and the alloy as casting can also be used. Usually, this alloy after casting is formed into products such as pipes by way of various processing steps such as forging, hot working and cold working. The alloy may be formed into products by powder metallurgical method. Heat treatment promotes the uniformity of the metal structure and contributes to improvements in the performance of the alloy of the present invention. In this case, the uniformization heat treatment is preferably carried out at 1100 to 1300°C, but the alloy as casting or processing can also be used.

Embodiment

[0038] Alloys with the chemical compositions shown in Table 1 were melt in a 50 kg vacuum high-frequency furnace, then formed by forging into plate materials with a thickness of 15 mm, and subjected to solution heat treatment at 1250°C and then test specimens were prepared.

Table 1

Table 1																		
(Weights, balance: Ni)																		
Symbol	C	Si	Mn	S	Cr	Al	N	B	Zr	Hf	Mo	W	Fe	Ta	Ca	W+Mo	Others	Division
1	0.025	0.15	0.08	0.0023	15.2	2.8	0.042	0.002	-	-	-	-	-	-	-	-	-	-
2	0.006	0.05	0.12	0.0001	15.9	3.1	0.001	0.004	-	-	10.4	-	4.8	1.2	0.002	10.4	-	-
3	0.010	1.85	0.25	0.0015	15.3	2.1	0.015	-	-	0.775	-	-	5.6	-	-	-	V: 0.1	-
4	0.012	0.19	0.68	0.0042	24.0	3.1	0.005	-	0.187	-	-	-	4.9	-	-	-	-	-
5	0.068	0.89	0.24	0.0002	14.9	2.8	0.002	0.003	0.020	-	-	-	9.2	-	-	-	Nb: 0.8	-
6	0.025	0.54	0.66	0.0010	18.5	3.5	0.008	0.002	-	-	-	10.5	4.5	0.5	-	10.5	Ti: 0.2, V: 0.02	-
7	0.066	0.24	0.90	0.0009	20.2	3.3	0.007	-	0.015	0.005	-	5.6	3.6	-	-	5.6	Ti: 0.2, V: 0.02	-
8	0.078	0.21	0.05	0.0005	16.4	3.4	0.011	0.004	-	-	-	-	0.2	-	-	-	La: 0.03	-
9	0.015	0.21	0.58	0.0003	19.8	2.5	0.010	0.025	-	-	8.7	4.5	6.8	-	0.002	13.2	La: 0.01, Ce: 0.02	-
10	0.006	0.35	0.18	0.0002	15.3	4.2	0.018	0.008	-	-	-	-	2.1	0.2	-	-	V: 0.1, Nb: 0.02	-
11	0.033	0.34	0.20	0.0010	14.5	3.0	0.024	0.003	-	-	12.2	-	3.9	-	-	12.2	Mg: 0.0035	-
12	0.011	0.09	0.15	0.0002	14.9	3.2	0.011	0.004	-	-	4.9	-	-	0.9	0.003	4.9	Nb: 0.5, V: 0.2	-
13	0.027	0.37	0.15	0.0008	13.8	2.6	0.005	0.004	-	-	7.5	-	0.2	1.7	0.002	7.5	Ti: 2.8, Nb: 0.2, Mg: 0.0052	-
14	0.027	0.37	0.64	0.0001	17.5	2.4	0.007	0.002	-	-	-	5.5	1.3	-	0.007	-	Y: 0.03	-
15	0.021	0.28	0.21	0.0002	16.5	1.7	0.015	0.002	-	-	-	-	2.1	-	-	-	Ti: 0.1	-
A	0.005	0.35	0.25	0.0001	20.5	1.1*	0.001	0.002	-	-	-	-	3.5	-	-	-	-	-
B	0.004	0.55	0.11	0.0005	15.4	5.5*	0.002	-	-	-	-	-	3.4	-	-	-	-	-
C	0.034	0.25	0.32	0.0074*	15.2	3.5	0.007	0.005	-	0.00	-	-	4.0	-	-	-	Y: 0.02	-
D	0.021	0.49	0.33	0.0008	15.4	3.3	0.065*	-	0.020	-	-	-	4.1	-	-	-	-	-
E	0.006	0.04	0.33	0.0003	15.4	3.3	0.014	-*	-*	-*	-	-	4.1	-	0.006	-	-	-
Comparative Examples																		

* shows the outside of the range defined in this invention.

[0039] To evaluate carburization resistance, high-temperature strength, hot workability and weldability, each test was conducted in the following manner.

(1) Pack carburization test (evaluation of carburization resistance)

Test specimen: 4 mm in thickness, 20 mm in width and 30 mm in length

Test method: A test specimen was inserted into a carburizing agent, heated at 1150°C and kept therein for 48 hours, and then the C content in the center in the direction of plate thickness of the test specimen was analyzed by inductively coupled plasma (ICP).

Evaluation: Judged to be excellent in carburization resistance when the amount of carburized C is 0.2% or less.

(2) Creep rupture test (evaluation of high-temperature strength)

Test specimen: 8.0 mm in diameter and 30 mm in mark distance

Test method: To measure an rupture time under the conditions of a temperature of 1150°C and a loading stress of 0.9 kgf/mm².

Evaluation: Judged to be excellent in high-temperature strength when the rupture time is 500 hours or more.

(3) Greeble test (evaluation of hot workability)

Test specimen: A round bar test specimen with a diameter of 10 mm in a parallel part and a length of 130 mm

Test method: After the specimen was heated at 1200°C for 5 minutes, cooled at 100°C/min. to 1000°C and then drawn at a strain rate of 5/s. After rupture, the sample was cooled with He gas, and then the reduction of area was measured.

Evaluation: Judged to be excellent in hot workability when the ratio of reduction of area is 60% or more.

(4) Longitude-varestraint test (evaluation of weldability)

Test specimen: 12 mm in thickness, 50 mm in width and 200 mm in length

Test method: The test specimen was subjected to TIG welding at an electric current of 200 A, a voltage of 17 V, and a welding rate of 15 cm/min. After that, 2% bending strain was applied to the specimen, to determine the total cracking length of the heat-affected zone (HAZ).

Evaluation: Judged to be excellent when the total cracking length is 5 mm or less.

[0040] The test results are shown in Table 2.

Table 2

Symbol	C amount (%)	Rupture time (hr)	Reduction of area (%)	Total cracking length (mm)	Division
1	0.13	542.5	61.4	5	Examples of the Invention
2	0.11	775.4	76.9	0	
3	0.10	550.6	73.5	3	
4	0.10	520.5	67.9	3	
5	0.13	598.5	74.0	1	
6	0.06	724.5	78.8	2	
7	0.10	650.2	72.5	2	
8	0.08	598.5	68.9	2	
9	0.19	768.9	80.5	1	
10	0.06	612.5	66.4	5	
11	0.12	770.3	65.4	4	
12	0.07	715.9	82.5	0	
13	0.18	812.5	67.8	3	
14	0.16	772.5	70.2	2	
15	0.18	550.0	85.6	0	
A	0.55	120.5	82.5	0	Comparative examples
B	0.05	535.5	25.0	20	
C	0.11	630.5	32.5	15	
D	0.14	580.9	49.8	12	
E	0.15	564.5	44.2	10	

[0041] As is evident from Table 2, the alloys 1 to 16 of the present invention containing Al in a range of 2.1 to less than 4.5% are excellent in any items of hot workability, carburization resistance, weldability and creep rupture strength. On the other hand, in the comparative alloy A whose C and Al contents are outside from the ranges defined in the present invention, the amount of carburized C is as significantly high as 0.55%, and the rupture time is as extremely short as 120 hours, and this alloy is not excellent in both carburization resistance and creep rupture strength. In addition, the comparative alloy B whose Al content exceeds the upper limit defined in the present invention shows a greeble reduction of area as low as 25%, and the total cracking length in the HAZ in the longitude-varestraint test is 20 mm, and this alloy can be seen to be inferior in both hot workability and weldability. In addition, both the comparative alloy C with a high S content and the comparative alloy D with a high N content are poor in hot workability and weldability. The comparative alloy E whose Cr content is less than the lower limit defined in the present invention is inferior in carburization resistance. Further, the comparative alloys F whose Si content is high and the comparative alloy G containing none of B, Zr and Hf are not excellent in hot workability and weldability.

INDUSTRIAL APPLICABILITY

[0042] The alloy of the present invention is an alloy having creep rupture strength satisfactory for use as a high-temperature strength member excellent in hot workability, weldability, carburization resistance and coking resistance. In particular, the alloy of the present invention demonstrates the above-described excellent characteristics under the environment of thermal cracking and heating cycle where carburization, oxidation and temperature change are repeated such as in pipes used particularly in ethylene cracking furnaces. As a result, the alloy of the present invention can be used to enable operation at a higher temperature, to prolong the period of continuous operation, and to extend the span for replacing with a new material due to the improvement of durability.

Claims

1. A heat resistant Ni base alloy comprising on a mass% basis:

C: 0.1% or less,
 Si: 2% or less,
 Mn: 2% or less,
 S: 0.005% or less,
 Cr: 10 to 25%,
 Al: 2.1 to less than 4.5%,
 N: 0.08% or less,
 0.001 to 1% in total of one or more elements of B: 0.03% or less, Zr: 0.2% or less and Hf: 0.3% or less,
 2.5 to 15% in total of one or more elements of Mo: 0.01 to 15% and W: 0.01 to 9%,
 Ti: 0 to 3%,
 Mg: 0 to 0.01%,
 Ca: 0 to 0.01%,
 Fe: 0 to 10%,
 Nb: 0 to 1%,
 V: 0 to 1%,
 Ta: 0 to 2%,
 Y: 0 to 0.1%,
 La: 0 to 0.1%,
 Ce: 0 to 0.1%,
 Nd: 0 to 0.1%,
 Cu: 0 to 5%,
 Co: 0 to 10%, and
 the balance being substantially Ni.

2. The heat resistant Ni base alloy according to claim 1, wherein the Ti content is 0.005 to 3% by mass.

3. The heat resistant Ni base alloy according to claim 1, wherein the Ti content is 0.005 to 3% and either one or both of Mg and Ca are contained in an amount of 0.0005 to 0.01% and 0.0005 to 0.01%, respectively.

4. The heat resistant Ni base alloy according to claim 1, wherein the Ti content is 0.005 to 3%, either one or both of

Mg and Ca are contained in an amount of 0.0005 to 0.01% and 0.0005 to 0.01%, respectively and the Fe content is 0.1 to 10%.

5. A heat resistant Ni base alloy comprising on a mass% basis,

C: 0.07% or less,

Si: 0.01 to 1%,

Mn: 1% or less,

S: 0.0025% or less,

Cr: 12 to 19%,

Al: 2.1 to less than 3.8%,

N: 0.045% or less,

0.001 to 1% in total of one or more metals of B: 0.03% or less, Zr: 0.2% or less and Hf: 0.8 or less,

Mo: 2.5 to 12%,

Ti: 0.005 to 1%,

Ca: 0.0005 to 0.01%,

Fe: 0.1 to 10%, and

the balance being essentially Ni.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 40 1832

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	PATENT ABSTRACTS OF JAPAN vol. 004, no. 129 (C-024), 10 September 1980 (1980-09-10) - & JP 55 082738 A (HITACHI LTD), 21 June 1980 (1980-06-21) * table, sample 4 * * abstract *	1,2	C22C19/05
Y	---	3,4	
Y	WO 95 27803 A (HOSKINS MFG CO) 19 October 1995 (1995-10-19) * claim 18; abstract *	3,4	
X	RYBNIKOV A I ET AL: "Service life of heat-resistant alloys with protective coatings in thermocyclic loading" SURFACE AND COATINGS TECHNOLOGY, JAN. 1996, ELSEVIER, SWITZERLAND, vol. 78, no. 1-3, pages 103-112, XP000940850 ISSN: 0257-8972 * table 2 *	1	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
A	US 2 515 185 A (BIEBER CLARENCE GEORGE ET AL) 18 July 1950 (1950-07-18) * col.3, ex.1; claim 1 *	1,2	C22C
A	PATENT ABSTRACTS OF JAPAN vol. 003, no. 037 (C-041), 29 March 1979 (1979-03-29) - & JP 54 014311 A (MITSUBISHI METAL CORP), 2 February 1979 (1979-02-02) * composition on page 3 * * abstract *	1	
A,D	US 4 671 931 A (HERCHENROEDER ROBERT B ET AL) 9 June 1987 (1987-06-09) * table 1; claim 1 *	1	
		-/-	
The present search report has been drawn up for all claims			
Place of search		Date of completion of the search	Examiner
MUNICH		29 September 2000	Bjoerk, P
CATEGORY OF CITED DOCUMENTS		T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application I: document cited for other reasons	
X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background C: non-written disclosure P: intermediate document		&: member of the same patent family, corresponding document	



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 40 1832

DOCUMENTS CONSIDERED TO BE RELEVANT			CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	
A,D	PATENT ABSTRACTS OF JAPAN vol. 017, no. 704 (C-1146), 22 December 1993 (1993-12-22) - & JP 05 239577 A (SUMITOMO METAL IND LTD), 17 September 1993 (1993-09-17) * table 1 * * abstract *	1,2	
A,D	DATABASE WPI Section Ch, Week 198211 Derwent Publications Ltd., London, GB; Class M27, AN 1982-20871E XP002148828 & JP 57 023050 A (SUMITOMO CHEM CO LTD), 6 February 1982 (1982-02-06) * abstract *	1	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search	Date of completion of the search	Examiner	
MUNICH	29 September 2000	Bjoerk, P	
CATEGORY OF CITED DOCUMENTS		I : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 40 1832

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

29-09-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 55082738 A	21-06-1980	NONE	
WO 9527803 A	19-10-1995	AU 2158895 A US 6093369 A	30-10-1995 25-07-2000
US 2515185 A	18-07-1950	NONE	
JP 54014311 A	02-02-1979	JP 1222725 C JP 58021001 B	15-08-1984 26-04-1983
US 4671931 A	09-06-1987	CA 1255928 A FR 2564107 A GB 2158461 A, B IN 164157 A IT 1184554 B JP 60238434 A NL 8500901 A	20-06-1989 15-11-1985 13-11-1985 21-01-1989 28-10-1987 27-11-1985 02-12-1985
JP 05239577 A	17-09-1993	NONE	
JP 57023050 A	06-02-1982	JP 1052465 B JP 1608295 C	08-11-1989 28-06-1991